

■

Amendments to the Claims:

Please amend the claims as follows.

1. (currently amended) A rare-earth sintered magnet of a composition of  $(R1_x + R2_y)T_{100-x-y-z}Q_z$ , where R1 is at least one element selected from the group consisting of all rare-earth elements excluding La, Y and Sc, R2 is ~~at least one element selected from the group consisting of La, Y and Sc~~ Y and may optionally include La and/or Sc, T is at least one element selected from the group consisting of all transition elements, and Q is ~~at least one element selected from the group consisting of B and C~~ B and may optionally include C, and comprising a crystal grain of an  $Nd_2Fe_{14}B$  type compound as a main phase, wherein:

molar fractions x, y and z satisfy

$$8 \leq x \leq 18 \text{ at\%},$$

$$0.1 \leq y \leq 3.5 \text{ at\% and}$$

$$3 \leq z \leq 20 \text{ at\%, respectively; and}$$

a concentration of R2 is higher in at least a part of a grain boundary phase than in the crystal grain, and

wherein an amount of oxygen is in a range of 2000 ppm to 8000 ppm by weight.

2. (original) The rare-earth sintered magnet according to claim 1, wherein the molar fractions x and y satisfy  $0.01 \leq y/(x+y) \leq 0.23$ .

3. (canceled)

4. (canceled)

25. (currently amended) A method of producing a rare-earth sintered magnet, comprising the steps of:

A4 preparing a powder of a rare-earth alloy having a composition of  $(R1_x + R2_y)T_{100-x-y-z}Q_z$  where R1 is at least one element selected from the group consisting of all rare-earth elements excluding La, Y and Sc; R2 is ~~at least one element selected from the group consisting of La, Y and Sc~~ Y and may optionally include La and/or Sc; T is at least one element selected from the group consisting of all transition elements; and Q is ~~at least one element selected from the group consisting of B and C~~ B and may optionally include C, wherein molar fractions x, y and z satisfy  $8 \leq x \leq 18$  at%,  $0.1 \leq y \leq 3.5$  at% and  $3 \leq z \leq 20$  at%, respectively, and wherein an amount of oxygen included in the rare-earth alloy powder is in a range of 2000 ppm by weight to 8000 ppm by weight; and

sintering the rare-earth alloy powder,

wherein R2 existing in a main phase crystal grain of an  $Nd_2Fe_{14}B$  crystalline structure in the rare-earth alloy before sintering is diffused into a grain boundary phase in the sintering step, whereby a concentration of R2 is higher in at least a part of the grain boundary phase than in the crystal grain.

6. (canceled)

47. (original) The method of producing a rare-earth sintered magnet according to claim 3, wherein R1 existing in the grain boundary phase in the rare-earth alloy before sintering is diffused into the main phase crystal grain during the sintering step.

38. (original) The method of producing a rare-earth sintered magnet according to claim 3, wherein an oxide of R2 is formed in the grain boundary phase during the sintering step.

16. (original) The method of producing a rare-earth sintered magnet according to claim 3, wherein the sintering step comprises a first step of maintaining the rare-earth alloy powder at a temperature in a range of 650 to 1000°C for 10 to 240 minutes, and a second step of further sintering the rare-earth alloy powder at a temperature higher than that used in the first step.

A4 17. (original) The method of producing a rare-earth sintered magnet according to claim 3, wherein the rare-earth alloy powder is obtained through pulverization in a gas whose oxygen concentration is controlled.

18. (original) The method of producing a rare-earth sintered magnet according to claim 3, wherein the rare-earth alloy powder is obtained through pulverization in a gas whose oxygen concentration is controlled to be 20000 ppm or less.

9 19. (original) The method of producing a rare-earth sintered magnet according to claim 3, wherein an average particle diameter (FSSS particle size) of the rare-earth alloy powder is 5 μm or less.

10 20. (currently amended) A rare-earth sintered magnet, having a composition of  $(R1_x + R2_y)(T1_p + T2_q)_{100-x-y-z-r}Q_zM_r$  where R1 is at least one element selected from the group consisting of all rare-earth elements excluding La, Y and Sc, R2 is at least one element selected from the group consisting of La, Y and Sc, Y and may optionally include La and/or Sc; T1 is Fe, T2 is at least one element selected from the group consisting of all transition elements excluding Fe, Q is at least one element selected from the group consisting of B and C, B and may optionally include C, and M is at

least one element selected from the group consisting of Al, Ga, Sn and In, and comprising a crystal grain of an  $\text{Nd}_2\text{Fe}_{14}\text{B}$  type compound as a main phase, wherein:

molar fractions x, y, z, p, q and r satisfy

$$8 \leq x+y \leq 18 \text{ at}\%,$$

$$0 < y \leq 4 \text{ at}\%,$$

$$3 \leq z \leq 20 \text{ at}\%,$$

$$0 < q \leq 20 \text{ at}\%,$$

$$0 \leq q/(p+q) \leq 0.3 \text{ at}\% \text{ and}$$

$$0 \leq r \leq 3 \text{ at}\%, \text{ respectively; and}$$

wherein an amount of oxygen is in a range of 2000 ppm to 8000 ppm by weight and a concentration of R2 is higher in at least a part of a grain boundary phase than in the crystal grain.

14. (original) The rare-earth sintered magnet according to claim 10, wherein the molar fraction y satisfies  $0.5 < y \leq 3 \text{ at}\%$ .

15. (canceled)

16. (original) The rare-earth sintered magnet according to claim 10, wherein T2 includes at least Co.

17. (canceled)

18. (currently amended) A method of producing a rare-earth sintered magnet, comprising the steps of:

preparing a powder of a rare-earth alloy having a composition of  $(\text{R1}_x + \text{R2}_y)(\text{T1}_p + \text{T2}_q)_{100-x-y-z-r}\text{Q}_z\text{M}_r$  where R1 is at least one element selected from the group consisting of all rare-earth elements excluding La, Y and Sc, R2 is at least one

~~element selected from the group consisting of La, Y and Sc~~ Y and may optionally include La and/or Sc; T1 is Fe, T2 is at least one element selected from the group consisting of all transition elements excluding Fe, Q is ~~at least one element selected from the group consisting of B and C~~ B and may optionally include C, and M is at least one element selected from the group consisting of Al, Ga, Sn and In), and comprising, as a main phase, a crystal grain of an Nd<sub>2</sub>Fe<sub>14</sub>B crystalline structure, wherein:

molar fractions x, y, z, p, q and r satisfy

$$8 \leq x+y \leq 18 \text{ at\%,}$$

$$0 < y \leq 4 \text{ at\%,}$$

$$3 \leq z \leq 20 \text{ at\%,}$$

$$0 < q \leq 20 \text{ at\%,}$$

$$0 \leq q/(p+q) \leq 0.3 \text{ at\% and}$$

$$0 \leq r \leq 3 \text{ at\%, respectively, and}$$

wherein an amount of oxygen included in the rare-earth alloy powder is in a range of 2000 ppm by weight to 8000 ppm by weight; and

sintering the rare-earth alloy powder,

wherein R2 existing in the main phase crystal grain of the Nd<sub>2</sub>Fe<sub>14</sub>B crystalline structure in the rare-earth alloy before sintering is diffused into a grain boundary phase in the sintering step, whereby a concentration of R2 is higher in at least a part of the grain boundary phase than in the crystal grain.

19. (canceled)

20. (original) The method of producing a rare-earth sintered magnet according to claim 18, wherein R1 existing in the grain boundary phase in the rare-earth alloy before sintering is diffused into the main phase crystal grain during the sintering step.

~~15~~  
~~21~~ (original) The method of producing a rare-earth sintered magnet according to claim ~~18~~<sup>13</sup>, wherein an oxide of R2 is formed in the grain boundary phase in the sintering step.

A4 ~~16~~  
~~22~~ (original) The method of producing a rare-earth sintered magnet according to claim ~~18~~<sup>13</sup>, wherein the sintering step comprises a first step of maintaining the rare-earth alloy powder at a temperature in a range of 650 to 1000°C for 10 to 240 minutes, and a second step of further sintering the rare-earth alloy powder at a temperature higher than that used in the first step.

~~17~~  
~~23~~ (original) The method of producing a rare-earth sintered magnet according to claim ~~18~~<sup>13</sup>, wherein the rare-earth alloy powder is obtained through pulverization in a gas whose oxygen concentration is controlled.

~~18~~  
~~24~~ (original) The method of producing a rare-earth sintered magnet according to claim ~~18~~<sup>13</sup>, wherein the rare-earth alloy powder is obtained through pulverization in a gas whose oxygen concentration is controlled to be 20000 ppm or less.

~~19~~  
~~25~~ (original) The method of producing a rare-earth sintered magnet according to claim ~~18~~<sup>13</sup>, wherein an average particle diameter (FSSS particle size) of the rare-earth alloy powder is 5 μm or less.

---